

NaF3000 Series of products

Features of NaF3000 Series

- NaF3000 series are ceramic-filled PTFE high-frequency copper clad laminates (CCLs) independently developed and produced by NaF-T.
- The dielectric constant is very stable and the dielectric loss is ultra low (D_k : 3.0~10.2; D_f : 0.00098~0.0023).

▶ Consistent and stable

▶ High peel strength

▶ Low dielectric loss

▶ Excellent cost performance

Application Fields of NaF3000 Series

- The Products are used in antenna, millimeter wave, military radar, military electronics, missile antenna, etc.
- NaF-T not only produces high-frequency copper clad laminates (CCLs) with ultra low loss, but also can customize the thickness and thermal conductivity of CCLs according to customer's needs.

▶ Space wideband antenna

▶ Missile antenna

▶ Microstrip and strip-line circuits

▶ Base station antenna

▶ Millimeter wave equipment

▶ Phase shifter

▶ Military radar

▶ High-frequency power divider

▶ Phased array radar

▶ IoT devices



NaF3062G: A PTFE RF Circuit Material with Woven Fiberglass Reinforcement

GENERAL PROPERTIES

Property	Typical Value	Direction	Unit	Condition	Test Method
Dielectric Constant, D_k	6.2±0.15	Z	-	10 GHz 23°C	IPC-TM-650 2.5.5.5 SPDR
Dissipation Factor, D_f	0.0018	Z	-	10 GHz 23°C	IPC-TM-650 2.5.5.5
Thermal Coefficient of ϵ_r	-80	Z	ppm/°C	10 GHz 0-100°C	IPC-TM-650 2.5.5.5
Dimensional Stability	-0.35,-0.40	X, Y	mm/m	COND A	IPC-TM-650 2.2.4
Volume Resistivity	10 ⁸		MΩ•cm	COND A	IPC 2.5.17.1
Surface Resistivity	10 ⁸		MΩ	COND A	IPC 2.5.17.1
Tensile Modulus	2000 2100	MD CMD	MPa	23°C	ASTM D638
Water Absorption	0.03	-	%	D48/50	IPC-TM-650 2.6.2.1
Thermal Conductivity	1.2	-	W/(m•K)	50°C	ASTM D5470
Coefficient of Thermal Expansion	10,10,35	X, Y, Z	ppm/°C	23°C/50% RH (23 ~ 288 °C)	IPC-TM-650 2.4.24
T_d	500		°C	TGA	ASTM D3850
Density	2.9		mg/cm ³		
Copper Peel Strength	10.0		pli	1 oz. EDC After floating tin	IPC-TM-2.4.8
Flammability	V-0				UL 94
Lead Free Process Compatible	YES				

PRODUCT SPECIFICATION

Standard Thickness	Standard Panel Size	Standard Copper Cladding
0.020" (0.508mm) +/- 0.0020" 0.030" (0.762mm) +/- 0.0030" 0.060" (1.016mm) +/- 0.0030" * Other thicknesses are available	12" X 18" (305 X 457mm) 24" X 18" (610 X 457mm)	Electrolytic copper foil:LP/VLP/RTF/HVLP ½ oz.(18µm) H/H 1 oz.(35µm) 1/1 * Additional cladding weights are available

Note: All typical values listed above are for reference only and not for specification.